## EverGuard® TPO 45 mil Membrane Data Sheet

Updated: 6/18



## EverGuard® TPO 45 mil Membrane

## **Applicable Standards**

 $\begin{array}{l} \mbox{UL Listed, FM Approved, Miami-Dade County Product Control Approved, State of Florida Approved, CRRC Rated, Title 24 \\ \mbox{Compliant}^*, \mbox{ENERGY STAR}^{\mbox{\$}} \mbox{Certified}^{**}, \mbox{ASTM D6878}. \end{array}$ 

Physical Properties	ASTM Test Method	ASTM D6878 Minimum	EverGuard® Typical Test Data	
Certain data is provided in MI Data is based upon typical pro	O (machine direction) × CMD (cross machine direction) duct performance, and is subject to normal manufa	on) format. acturing tolerance and variance.		
Nominal Thickness	ASTM D751	0.039" (min.) (0.99 mm)	0.045" (1.14 mm)	
Breaking Strength	ASTM D751 Grab Method	220 lbf/in. (38.5 kn/m)	280 lbf x 270 lbf (417.2 x 402.3 kg/m	
Factory Seam Strength	ASTM D751	66 lbf (98.34 kg/m)	110 lbf (membrane failure) (163.9 kg/m)	
Elongation at Break	ASTM D751	15%	30%	
Heat Aging	ASTM D573	90% Retention of Breaking Strength and Elongation at Break	100%	
Tear Strength	ASTM D751 8" x 8" (203 x 203 mm) Sample	55 lbf (81.95 kg/m)	100 lbf x 120 lbf (149 x 178.8 kg/m)	
Puncture Resistance	FTM 101C Method 2031	Not Established	290 lb. (131 kg)	
Cold Brittleness	ASTM D2137	-40°C	-40°C	
Permeance	ASTM E96	Not Established	O.O8 Perms	
Dimensional Change	ASTM D1204 @158°F (70°C), 6 hrs.	+/-1%	0.4%	
Water Absorption	ASTM D471 @158°F (70°C), 1 week	+/-3.0% max.	0.7%	
Hydrostatic Resistance	ASTM D751 Method D	Not Established	380 psi	
Ozone Resistance	ASTM D1149	No visible deterioration @ 7 x magnification	No visible deterioration @ 7 x magnification	
SRI (Solar Reflectance Index) Initial/Aged	N/A	N/A	94/81 83 Aged Title 24	
Reflectivity (white) Initial/Aged	ASTM C1549 ASTM E903	N/A N/A	0.76/0.68 81.9% Reflectance	
Emissivity (white) Initial/Aged	ASTM C1371 ASTM E403	N/A N/A	0.90/0.83 0.94	
Weather Resistance	ASTM G155/D6878	10,080 KJ/(m² · nm) at 340 nm	>20,000 KJ/(m²·nm) at 340 nm	
Heat Aging	ASTM D573	240°F (115°C) for 32 weeks	60 weeks	
Thickness Above Scrim	ASTM D7635	Min 30% of Total Thickness	15.8 mil (Nominal)	
Guarantee				
Up to 20 years			-	

<sup>\*</sup>White Membrane Only

## **Product Data**

	5′x 100′	6′ x100′	8'x100'	10′x100′	12′x100′			
Roll Size	(1.52 × 30.5 m) (500 sq. ft. [46.5 sq.m])	(1.83 × 30.5 m) (600 sq. ft. [55.74 sq.m])	(2.44 × 30.5 m) (800 sq. ft. [74.3 sq.m])		(3.65 × 30.5 m) (1,200 sq. ft. [111.484 sq.m])			
Roll Weight	128 lb. (58.1 kg)	153.6 lb. (69.7 kg)	204 lb. (93 kg)	256 lb. (116.1 kg)	307.2 lb. (139.3 kg)			
Colors	White, Tan, Gray							
Storage	Store rolls on their sides on pallets or shelving in a dry area.							
Safety Warning	Membrane rolls are heavy. Position and install by at least two people.							
Note: Membrane rolls shipped horizontally on pallets, stacked pyramid-style and banded. Product sizes, dimensions, and widths are nominal values and are subject to normal manufacturing/packaging tolerance and variation.								



<sup>\*\*</sup>ENERGY STAR® only valid in the U.S.