Monarplan GF Fleeceback

Monarplan GF Fleeceback is a Polyvinyl Chloride (PVC), glass reinforced single-ply roofing membrane with a polyester fleece backing.

APPLICATION

Monarplan GF Fleeceback is intended for use as an exposed membrane in fully adhered roofing systems. Membranes should be installed in accordance with the manufacturer's guidelines.

| Upper Surface | Smooth PVC surface - RAL7001 (grey) - RAL 7015 (anthracite) | |
|-----------------------|---|--|
| Lower Surface | Polyester fleece (250g/m²) | |
| Material | Polyvinyl Chloride (PVC) | |
| Type of Reinforcement | Glass fibre | |

| Characteristic | Test Method | Value or Statement | Tolerance | Units |
|------------------------------|-------------------|------------------------|-----------|---------|
| Length | BS EN 1848-2 | 15 | -0/+5% | m |
| Width | BS EN 1848-2 | 2.12 | -0/+5% | m |
| Mass per unit area | BS EN 1849-2 | 2.2 | -5/+10 % | kg·m² |
| Effective thickness | BS EN 1849-2 | 1.5 (+ fleece) | -5/+10 % | mm |
| Water tightness | BS EN 1928 (B) | pass | - | - |
| External fire performance* | BS EN 13501-5 | B _{ROOF} (t4) | - | - |
| Reaction to fire | BS EN 13501-1 | Class E | - | - |
| Tensile strength | BS EN 12311-2 (A) | ≥ 400 | - | N/50 mm |
| Elongation | BS EN 12311-2 (A) | ≥ 30 | - | % |
| Dimensional stability | BS EN 1107-1 | ≤ 0.3 | - | % |
| Water vapour diffusion value | EN 1931 | μ=14'000 | - | - |
| Resistance to impact | BS EN 12691 (B) | ≥ 500 | - | mm |
| Joint peel resistance | EN 12316-2 | ≥ 185 | - | N/50 mm |
| Resistance to Cold Blend | EN 495-5 | ≤ -30 | - | °C |
| | | | | |

MD = Machine Direction. TD = Transverse Direction.



^{*} The external fire performance is a system test, please contact BMI lcopal Technical Services to verify that the chosen system has the potential to meet your required performance prior to commencement.

PACKAGING

| Description | Roll Dimensions | Rolls per pallet | Product Code |
|------------------------------------|-----------------|------------------|--------------|
| Monarplan GF Fleeceback Anthracite | 15m x 2.12m | 9 | 10001399 |
| Monarplan GF Fleeceback Grey | 15m x 2.12m | 9 | 10001376 |

STORAGE

The membranes are delivered to site in rolls packed on pallets. Store and protect materials from mechanical damage and shelter from rain and sun. They must be stored horizontal on a flat surface and kept dry at a temperature between 0 °C and +40 °C. Materials temporarily kept outdoors or on the roof during construction should be given the same protection. Exercise caution and do not exceed the allowable live load of the structure.

INSTALLATION SUMMARY

Monarplan GF Fleeceback membranes are installed by adhesion. The membrane is to be installed in accordance with manufacturer's instructions and current and relevant standards such as BS 6229 and SPRA's Design Guide.

For further details please consult our Flat Roofing Product Installation Guidelines or contact our BMI Icopal technical services team.

TECHNICAL SERVICES

For further information and technical support, please contact our technical services team:

T: +44 (0) 330 123 4585

E: technical.uk@bmigroup.com

CERTIFICATION

Monarplan FM has been independently site and laboratory tested by the British Board of Agrément, and awarded BBA certificate number 10/4739 (PS2).





SAFETY, QUALITY & ENVIRONMENT

BMI Icopal synthetic membranes are distributed under a Quality Management System approved to ISO 9001: 2015 and an Environmental Management System approved to ISO 14001: 2015, by TÜV NORD CERT GmbH.

Information regarding transportation, handling, storage and disposal can be found on the Safety Data Sheets.







BMI Group UK Limited

BMI House, 2 Pitfield, Kiln Farm, Milton Keynes, MK11 3LW bmigroup.com/uk

Product, technical standards and codes of practice are under constant review. We reserve the right to change and amend products and information without prior notice. For the latest information, suitability and specification advice, please contact BMI Icopal technical services team.