Xtra-Gard Flexitorch P Torch On Mineral Capsheet

Xtra-Gard Flexitorch P is a polyester reinforced SBS-modified bitumen membrane.

APPLICATION

Xtra-Gard Flexitorch P is intended for use as a torch-applied top sheet in a bitumen built-up roof system. Membranes should be installed in accordance with the manufacturer's guidelines.

Upper Surface	Mineral granules with thermofusible PE film to overlap selvedge		
Lower Surface	Thermofusible PE film		
Material	SBS-Modified Bitumen		
Type of Reinforcement	Polyester 195g/m²		

Characteristic	Test Method	Value or Statement	Tolerance	Units
Length	EN 1848-1	8	±0.1	m
Width (inc. Selvedge)	EN 1848-1	1	±0.02	m
Mass per unit area	BS EN 1849-1	4.94	±0.15	kg∙m²
Effective thickness	BS EN 1849-1	3.8	±0.2	mm
Water tightness	BS EN 1928 (B)	Pass	-	-
External fire performance*	BS EN 13501-5	B _{ROOF} (t4)	-	-
Tensile strength	BS EN 12311-1	700 (MD); 600 (TD)	±35%	N/50 mm
Elongation	BS EN 12311-1	22 (MD); 27 (TD)	±35%	%
Dimensional stability	BS EN 1107-1	≤ 0.5	-	%
Flexibility at low temperature	BS EN 1109	≤ -10	-	°C
Flow resistance at elev. temp	BS EN 1110	> 105	-	°C

MD = Machine Direction. TD = Transverse Direction.

BMI icopal

* The external fire performance of a roof is tested as a built-up roof system and therefore no performance can be determined from any single product alone. Please consult BMI lcopal technical services for system specific information prior to commencing construction.

PACKAGING

Description	Roll Dimensions	Rolls per pallet	Product Code
Xtra-Gard Flexitorch P Charcoal	8m x 1m	25	10001206
Xtra-Gard Flexitorch P Green	8m x 1m	25	10001179

STORAGE

Materials for reinforced bitumen membrane roofing should be stored upright on clean dry level surfaces, undercover and clear of the ground. The same protection should be given to materials temporarily kept outdoors or on the roof during construction. Storage temperatures should be between 0°C and 30°C. Refer to BS 8000-4 (Section 2.1.2.2) for further information.

INSTALLATION SUMMARY

Xtra-Gard Flexitorch P membranes are applied by torch-on application. The membrane is to be installed in accordance with current and relevant standards such as BS 8217, BS 6229 and BS 8000-4.

For further details please consult our Flat Roofing Product Installation Guidelines or contact our BMI Icopal technical services team.

TECHNICAL SERVICES

For further information and technical support, please contact our technical services team:

T: +44 (0) 330 123 4585 E: technical.uk@bmigroup.com

SAFETY, QUALITY & ENVIRONMENT

BMI Icopal membranes are manufactured under a Quality Management System approved to ISO 9001: 2015 and an Environmental Management System approved to ISO 14001: 2015 by TÜV NORD CERT GmbH.

Information regarding transportation, handling, storage and disposal can be found on the relevant Safety Data Sheet.







ISO 140 44 100 2

2797 CPR 5057



BMI Group UK Limited

BMI House, 2 Pitfield, Kiln Farm, Milton Keynes, MK11 3LW **bmigroup.com/uk**

Product, technical standards and codes of practice are under constant review. We reserve the right to change and amend products and information without prior notice. For the latest information, suitability and specification advice, please contact BMI lcopal technical services team.